

MOD.M510/11	<b>Test Report</b>	<b>ChemiLab</b>
Rev. 2/22-10-07		

Test report n. 24PI/08

**Consignor:**

DITTA Cartiera di Trevi SpA  
Via Clitunno, 4  
Borgo Trevi (PG)

<b>Sample of:</b>	No. 1 Medium Type cardboard	
<b>Taken by/on:</b>	Company technicians	05/05/2008
<b>Date of receipt:</b>	05/05/2008	
<b>Description:</b>	Physical state: solid	
	Colour: light brown	
	NOTES:	
<b>Date of test:</b>	Started: 10/05/2008	Ended: 26/05/2008

<b>METALS</b>	<b>CONCENTRATION Sq.m/Kg</b>	<b>CONCENTRATION LIMIT Sq.m/Kg</b>
Lead	16,76	-
Cadmium	1,39	-
Chrome (VI)	<0,01	-
Mercury	<0,01	-
<b>TOTAL</b>	<b>19,15</b>	<b>100</b>
Chrome total	(8,51)	-

**Norm of reference : D.L.vo n.22 5-2-97 : IRSA CNR Q.64 « Analitical methods for muds »  
Vol. 3; DM 18-6-79; DM 267 30-5-01**

Place: Foligno  
Date: 27 May 2008

The Laboratory chief  
Dr. Massimo Ciancaloni  
Chemists Guild LUAM n. 1437

MOD.M510/11	<b>Test Report</b>	<b>ChemiLab</b>
Rev. 2/22-10-07		

Test report n. 23PI/08

**Consignor:**

DITTA Cartiera di Trevi SpA  
Via Clitunno, 4  
Borgo Trevi (PG)

<b>Sample of:</b>	No. Semichemical use type cardboard	
<b>Taken by/on:</b>	Company technicians	05/05/2008
<b>Date of receipt:</b>	05/05/2008	
<b>Description:</b>	Physical state: solid	
	Colour: light brown	
	NOTES:	
<b>Date of test:</b>	Started: 10/05/2008	Ended: 26/05/2008

<b>METALS</b>	<b>CONCENTRATION Sq.m/Kg</b>	<b>CONCENTRATION LIMIT Sq.m/Kg</b>
Lead	11,93	-
Cadmium	1,13	-
Chrome (VI)	<0,01	-
Mercury	<0,01	-
<b>TOTAL</b>	<b>15,06</b>	<b>100</b>
Chrome total	(5,97)	-

**Norm of reference : D.L.vo n.22 5-2-97 : IRSA CNR Q.64 « Analitical methods for muds »  
Vol. 3; DM 18-6-79; DM 267 30-5-01**

Place: Foligno  
Date: 27 May 2008

The Laboratory chief  
Dr. Massimo Ciancaloni  
Chemists Guild LUAM n. 1437

MOD.M510/11	<b>Test Report</b>	ChemiLab
Rev. 2/22-10-07		

Test report n. 22PI/08

**Consignor:**

DITTA Cartiera di Trevi SpA  
Via Clitunno, 4  
Borgo Trevi (PG)

<b>Sample of:</b>	No. 1 Grey Board type cardboard	
<b>Taken by/on:</b>	Company technicians	05/05/2008
<b>Date of receipt:</b>	05/05/2008	
<b>Description:</b>	Physical state: solid	
	Colour: grey	
	NOTES:	
<b>Date of test:</b>	Started: 10/05/2008	Ended: 26/05/2008

<b>METALS</b>	<b>CONCENTRATION Sq.m/Kg</b>	<b>CONCENTRATION LIMIT Sq.m/Kg</b>
Lead	16,77	-
Cadmium	1,04	-
Chrome (VI)	<0,01	-
Mercury	<0,01	-
<b>TOTAL</b>	<b>17,81</b>	<b>100</b>
Chrome total	(7,45)	-

**Norm of reference : D.L.vo n.22 5-2-97 : IRSA CNR Q.64 « Analitical methods for muds »  
Vol. 3; DM 18-6-79; DM 267 30-5-01**

Place: Foligno  
Date: 27 May 2008

The Laboratory chief  
Dr. Massimo Ciancaloni  
Chemists Guild LUAM n. 1437

MOD.M510/11	<b>Test Report</b>	<b>ChemiLab</b>
Rev. 2/22-10-07		

Test report n. 21PI/08

**Consignor:**

DITTA Cartiera di Trevi SpA  
Via Clitunno, 4  
Borgo Trevi (PG)

<b>Sample of:</b>	No. 1 Honeycomb type cardboard	
<b>Taken by/on:</b>	Company technicians	05/05/2008
<b>Date of receipt:</b>	05/05/2008	
<b>Description:</b>	Physical state: solid	
	Colour: light brown	
	NOTES:	
<b>Date of test:</b>	Started: 10/05/2008	Ended: 26/05/2008

<b>METALS</b>	<b>CONCENTRATION Sq.m/Kg</b>	<b>CONCENTRATION LIMIT Sq.m/Kg</b>
Lead	17,34	-
Cadmium	1,36	-
Chrome (VI)	<0,01	-
Mercury	<0,01	-
<b>TOTAL</b>	<b>18,70</b>	<b>100</b>
Chrome total	(7,30)	-

**Norm of reference : D.L.vo n.22 5-2-97 : IRSA CNR Q.64 « Analitical methods for muds »  
Vol. 3; DM 18-6-79; DM 267 30-5-01**

Place: Foligno  
Date: 27 May 2008

The Laboratory chief  
Dr. Massimo Ciancaloni  
Chemists Guild LUAM n. 1437

MOD.M510/11	<b>Test Report</b>	<b>ChemiLab</b>
Rev. 2/22-10-07		

Test report n. 20PI/08

**Consignor:**

DITTA Cartiera di Trevi SpA  
Via Clitunno, 4  
Borgo Trevi (PG)

<b>Sample of:</b>	No. 1 Kraft type cardboard	
<b>Taken by/on:</b>	Company technicians	05/05/2008
<b>Date of receipt:</b>	05/05/2008	
<b>Description:</b>	Physical state: solid	
	Colour: light	
	NOTES:	
<b>Date of test:</b>	Started: 10/05/2008	Ended: 26/05/2008

<b>METALS</b>	<b>CONCENTRATION Sq.m/Kg</b>	<b>CONCENTRATION LIMIT Sq.m/Kg</b>
Lead	20,79	-
Cadmium	1,87	-
Chrome (VI)	<0,01	-
Mercury	<0,01	-
<b>TOTAL</b>	<b>22,66</b>	<b>100</b>
Chrome total	(7,13)	-

**Norm of reference : D.L.vo n.22 5-2-97 : IRSA CNR Q.64 « Analitical methods for muds »  
Vol. 3; DM 18-6-79; DM 267 30-5-01**

Place: Foligno  
Date: 27 May 2008

The Laboratory chief  
Dr. Massimo Ciancaloni  
Chemists Guild LUAM n. 1437